



1034 East New York Street
 Indianapolis, IN 46202
 317-879-2055
 800-593-0126
 www.ACCESSA.biz

Vinyl Wash Primer

Description: A two-component, pre-treatment bonding primer which will assure adhesion to almost any non-ferrous surface (aluminum, copper, brass, magnesium and ceramic tile), ferrous metals and zinc-coated steel. Compatible with a wide range of solvent-based topcoats.

Uses: All aluminum surfaces must be primed with Vinyl Wash. Examples include bleacher seats, aluminum boats, storm doors and windows, plus aluminum machine parts. Also suitable for ceramic bath tubs and bathroom tile before finishing. May be used on many other non-porous problem surfaces, in particular stainless steel, glass, etc.

Application: Spray application is almost essential due to extremely fast dry time and the importance of an even film. Airless tip size - .011, apply in one wet coat to .3-.5 mil DFT. This product will not spray electrostatically. Mixing, thinning and application instructions printed on the label are absolutely essential to the performance of Vinyl Wash.

Appearance: Transparent with a slight green color.

Coverage: Making sure to not apply greater than .5 mils dry, approximately 1000 sq. ft. per gallon.

Dry Times: Dry to touch – 20 minutes. Dry to recoat with any product – 30 minutes or until fingernail won't remove.

Flash Point: 53° F (tag closed cup)

Mixing Instructions: The mix ratio is one part 328-A to one part 328-B (1:1), by volume.

Pot Life: 6-8 hours.

Type	Dry Time		Solids		Coverage	VOC	Thinner	Clean Up
Vinyl	Recoat 30 mins.	Handle 20 min.	Wt A: 17.5% B: 18%	Vol A:9% B:8.6%	288 sq. ft./gal. @ .4 mils	5.98 lbs. per gln.	Product is pre- reduced via the 328-B.	Clean tools with 100% Isopropyl Alcohol.

ACCESSA Coatings Solutions makes no implied warranties of merchantability or fitness for a particular purpose with respect to this product. Customer's only remedy for any defect in this product is recovery of (1) the original cost including freight, plus (2) the unrecoverable value of the product to which the defective coating is applied. As a condition of any recovery, customer must take all reasonable steps to minimize their costs and losses as soon as it is discovered that the product is defective. In no event shall ACCESSA Coatings Solutions be liable to customer for any other consequential or incidental damages arising from or in connection with this product.